

Technical data

noraplan® ultra grip, surface: reflection-breaking



Carbon Neutral Floors™

	Test method	Requirements	Average test results from running production
CE conformity	EN 14041		Manufacturer: nora systems GmbH, D-69469 Weinheim
DoP-No.	EN 14041		0010
Thermal conductivity	EN 10456	$\lambda = 0.17 \text{ W/(m·K)}$	Fulfilled
Dynamic coefficient of friction	EN 13893	DS	Fulfilled
Reaction to fire	EN 13501-1	Not bonded	C _r -s1
Reaction to fire	EN 13501-1	Bonded on mineral subfloor	C _r -s1

Properties acc. to EN 1817

Thickness	EN ISO 24346	Mean value ± 0.15 mm acc. to EN 1817	2.0 mm
Dimensional stability	EN ISO 23999	± 0.4 %	± 0.3 %
Cigarette-burn resistance	EN 1399	Procedure A (stubbed out) \geq level 4 Procedure B (burning) \geq level 3	Fulfilled
Flexibility	EN ISO 24344, procedure A	Mandrel diameter 20 mm, no fissuring	Fulfilled
Hardness	ISO 48-4	≥ 75 Shore A acc. to EN 1817	90 Shore A
Residual indentation	EN ISO 24343	Mean value ≤ 0.15 mm at thickness < 2.5 mm	0.05 mm
Abrasion resistance at 5 N load	ISO 4649, procedure A	≤ 250 mm ³	90 mm ³
Colour fastness to artificial light	ISO 105-B02, procedure 3, test conditions 6.1 a)	At least level 6 on the blue scale; \geq level 3 on the grey scale	Grey scale \geq level 3 acc. to ISO 105-A02
Classification	EN ISO 10874	Commercial / Industrial	34 / 42

Additional technical properties

Toxicity of fire gases	DIN 53436		Carbonisation gases are non-toxic
Anti-slip properties	DIN EN 16165	Acc. to DGUV 108-003	R 11
	BS 7976 TRRL Pendulum		A; B; C
	SATRA TM 144		36+
			Wet & Dry
Improvement in footfall sound absorption	ISO 10140-3		Wet: > 0.6 Dry: > 0.45
Effect of chemicals	ISO 10140-3		7 dB
Effect of chemicals	EN ISO 26987		Resistant depending on concentration and time of exposure*
Electrical insulation properties	EN 1081 R1		$> 10^9$ Ohm
Electrical propensity when walked upon	EN 1815		Antistatic, charging in case of rubber soles < 2 kV
Effect of a castor chair	EN ISO 4918		Suitable if castor wheels, type W, acc. to EN 12529, are used
Underfloor heating	EN 1264-2		Suitable, max. 35 C°

* In case of increased impact of oils, grease, acids, alkalis and other aggressive chemicals please contact us.

EN 1817: Specification for homogeneous and heterogeneous smooth elastomer floor coverings

Colour variations due to different production batches as well as technical alterations to improve the product have to be accepted.

