

noraplan linee™

SHEET

Rubber floor covering with a linear pattern and surface profile that bring subtle dimension to the floor while both accentuating and supporting the muted colorway.

- Good for heavy traffic
- Superior footfall sound absorption
- Excellent slip resistance
- Increased safety thanks to high fire-retardant properties
- Seamless installation
- No coatings needed



Product Data

| | |
|-----------------|---|
| Product | noraplan linee™ 2.0 mm sheet resilient floor covering, Article 160E |
| Description | nora® vulcanized rubber compound 913 with environmentally compatible color pigments that are free of toxic heavy metals like lead, cadmium, or mercury. |
| Characteristics | Material Dimensions: 49.21 feet x 48 inches (15 m x 1.22 m) Thickness: 0.08 inches (2.0 mm) Dimensional Stability: Meets requirements Composition: Homogeneous rubber compound Colors: 10 Standard Surface: Striated profile |

Technical Data

| | |
|---------------------|--|
| Static Load Limit | ASTM F970, Residual compression of 0.002" with 800 lbs. ≤ 0.005" with 250 lbs. is required |
| Rolling Load Limit | ASTM F2753, ≤ 450 lbs. /sq. inch; no forklift traffic |
| Slip Resistance | ASTM D2047 Static coefficient of friction, Neolite dry 0.85 Neolite wet 0.75 ≥ 0.5 is required (not recommended for ramps), |
| Flammability | ASTM E648; NFPA 253; NBSIR 75 950, 0.98 Class 1, ≥ 0.45 watts/sq. cm is required |
| Smoke Density | ASTM E662; NFPA 258; NBS, 134 (flaming) and 109 (non-flaming) < 450 is required |
| Bacteria Resistance | ASTM E2180 and ASTM G21, resistant to bacteria, fungi, and micro-organism activity |
| Sound Absorption | ISO 140, Δ Lw8dB (compare only Δ values) |
| Hardness | ASTM D2240, Shore type "A", 92 achieved, ≥ 85 is required |
| CAN/ULC-S102.2 | Surface Burning, FSC1 of 125 and SD of 370 |

Health & Environmental

| | |
|---------------------------------|--|
| Carbon Neutral Floors | All flooring products 3rd party verified carbon neutral throughout their entire life cycle through the Interface Carbon Neutral Floors™ program. Learn more at www.interface.com/carbonneutral . |
| Indoor Air Quality | Greenguard Gold Certified for low VOC Emissions in compliance with CDPH 01350 |
| Material Composition | Free of Added Formaldehyde, Heavy Metals and Ortho Phthalates, Fluorinated Chemicals (PFAS), and Halogenated Flame Retardants. |
| Transparency | Cradle to Cradle v3.1 Silver, Environmental Product Declarations (EPDs), and Health Product Declarations (HPDs) available for all standard norament and noraplan floor coverings. Learn more at www.nora.com/us . |
| Production Plant Certifications | ISO 9001:2000 ISO 14001 |

Installation

| | |
|------------------------|--|
| Site Conditions | The installation area must be fully enclosed, weather tight, and climate controlled between 63°F and 75°F and 40% to 60% ambient relative humidity (RH) for at least 48 hours prior, during and 72 hours after installation. |
| Adhesive | Absorptive substrates: use nora® AC 100 or nora dryfix™ 750 adhesives Non-absorptive substrates: use nora dryfix 750 adhesive |
| Unique Characteristics | Welding not required |

For complete installation instructions, refer to the nora® Installation Instructions.

Care and Cleaning

Refer to the noraplan® Maintenance Guidelines.

Wheel Types

No metal or hard plastic wheels, the shape of the contact surface of wheels must be flat with round edges. The shore hardness must be ≤ 90 type A.

Storage

nora® flooring can be stored within a temperature range of -5°F (-21°C) to 120°F (49°C) under the following conditions: Pallets shall remain intact, undamaged, not be stacked, be in a permanently dry environment, and with no direct sunlight. However, all adhesives and cold weld must remain at room temperature without freezing.

Warranty

Limited 5-year warranty. See nora® Limited Warranty.

For current nora® Installation Instructions, Guide Specifications, Maintenance Guidelines, and Limited Warranties, please visit www.nora.com/us.

Updated: March 2021

nora systems, Inc.

9 Northeastern Blvd.
Salem, NH 03079
Toll free: 800-332-NORA
Phone: (603) 894-1021
Fax: (603) 894-6615
E-mail: info-us@nora.com
www.nora.com/us