

nora[®] PRN 102

PRIMER (non-absorptive substrates)

nora[®] PRN 102 is an acrylic primer with carbon fiber technology for wood and/or non-absorptive substrates. Used as a bonding agent on dense and smooth substrates for nora L 1000 leveler and nora SP 111 patch.

- Water based
- Solvent free
- Meets the South Coast (CA) Air Quality Management District Rule 1168



Product Data

Product	nora [®] PRN 102, Article 6700
Description	nora PRN 102 is a fast drying primer for non-absorptive substrates.
Characteristics	White liquid; 1.12 gallon white container

Technical Data

Shelf Life	12 Months
Application	micro fiber roller
Coverage	~ 520 – 785 sq. ft. per 1.12 gallon unit
Storage	Room temperature and away from direct sunlight
Moisture Limit	≤ 85% RH following ASTM F2170 <i>Standard Test Method for Determining Relative Humidity in Concrete Floor Slabs Using in situ Probes</i>
Freeze/Thaw stable	Keep from freezing

Environmental Attributes

VOC Content	< 19 grams/liter; product is in compliance with the SCAQMD Rule 1168 Standard for Architectural sealants, which has a VOC limit of 250 grams/liter
LEED Contribution	Meets VOC content requirements of LEED

Installation Requirements

Site Conditions	The installation area must be fully enclosed, weather tight, and climate controlled between 63°F and 75°F and 40% to 60% ambient relative humidity (RH) for at least 48 hours prior, during and 72 hours after installation.
Substrate Requirements	Clean non-absorptive substrates. Plywood. Refer to the nora [®] Installation Guide for details.
Unique Characteristics	Do not dilute

For complete installation instructions, refer to the nora Installation Guide.

Disclaimer

It is the user's responsibility to read, understand and follow the nora Installation Guide, Product Data Sheet and Safety Data Sheet available on www.nora.com/us. You should comply with all applicable OSHA, local, state and federal regulations.

Clean-up

Immediately clean from tools and surfaces using soap, water and a clean cloth or 70% Isopropyl alcohol. Once cured, dried primer can only be mechanically removed.

Disposal

Dispose in accordance with local, state and federal regulations.

Traffic

Foot traffic is allowed after dry and tack free, ~ 30 to 90 minutes.

Warranty

See nora® Limited Warranty.

For current nora® Installation Guides, Guide Specifications, Maintenance Guides, and Limited Warranties, please visit www.nora.com/us.

Dated: November 2018

nora systems, Inc.

9 Northeastern Blvd.

Salem, NH 03079

Toll free: 800-332-NORA

Phone: (603) 894-1021

Fax: (603) 894-6615

E-mail: info-us@nora.com

www.nora.com/us