


nora[®] stair nosings

STAIR ACCESSORY

Rubber nosings with a slide-in lip for installation on all types of staircases. For use with noraplan[®] or norament[®] floor coverings.

- Good for very heavy traffic
- Superior footfall sound absorption
- Excellent slip resistance
- Increased safety thanks to high fire-retardant properties
- VI inserts available
- No coatings needed



Product Data

Product	nora [®] stair nosings, Article 802 - T 5044 A/C, E/F Article 805 - T 5049 A/C, E/F
Description	nora [®] vulcanized rubber compound 96% natural fillers and environmentally compatible color pigments that are free of toxic heavy metals like lead, cadmium or mercury.
Characteristics	<p>Material Dimensions:</p> <p>Length: 8.2 feet (2.5 m)</p> <p>Depth: T 5049 2.0 inches (50 mm), T 5044 2.75 inches (70 mm)</p> <p>Height: T 5049 1.77 inches (45 mm), T 5044 1.69 inches (43 mm)</p> <p>Thickness: A/C 0.25 inches (6.5 mm), E/F 0.31 inches (8 mm)</p> <p>Composition: Homogeneous rubber compound</p> <p>Colors: 5 standard colors</p> <p>Surface: Smooth</p>

Technical Data

ASTM F1861	Type TP, rubber, Thermoplastic
Slip Resistance	ASTM D2047 Static coefficient of friction, Neolite dry 0.95 Neolite wet 0.94 ≥ 0.5 is required (not recommended for ramps)
Flammability	ASTM E648; NFPA 253; NBSIR 75 950, 0.52 Class 1, ≥ 0.45 watts/sq. cm is required
Smoke Density	ASTM E662; NFPA 256; NBS, 289 (flaming) and 273 (non-flaming) < 450 is required
Bacteria Resistance	ASTM E2180 and ASTM G21, resistant to bacteria, fungi, and micro-organism activity
Hardness	ASTM D2240, Shore type "A", 90 achieved ≥ 85 is required

Installation

Site Conditions	The installation area must be fully enclosed, weather tight, and climate controlled between 63°F and 75°F and 40% to 60% ambient relative humidity (RH) for at least 48 hours prior, during and 72 hours after installation.
Adhesive	Contact cement / nora® PU 102
Unique Characteristics	Allows for the installation of nora products on unusual stair designs

For complete installation instructions, refer to the nora® Installation Guide.

Care and Cleaning

Refer to the nora® Maintenance Guide – Stair Tread Maintenance.

Wheel Types

No metal or hard plastic wheels, the shape of the contact surface of wheels must be flat with round edges. The shore hardness must be type A \leq 90.

Storage

nora® flooring can be stored within a temperature range of -5°F (-21°C) to 120°F (49°C) under the following conditions: Pallets shall remain intact, undamaged, not be stacked, be in a permanently dry environment, and with no direct sunlight. However, all adhesives and cold weld must remain at room temperature without freezing.

Warranty

Limited 1 year defect warranty. See nora® Limited Warranty.

For current nora® Installation Guides, Guide Specifications, Maintenance Guides, and Limited Warranties, please visit www.nora.com/us.

Updated: November 2018

nora systems, Inc.

9 Northeastern Blvd.
Salem, NH 03079
Toll free: 800-332-NORA
Phone: (603) 894-1021
Fax: (603) 894-6615
E-mail: info-us@nora.com
www.nora.com/us