

# nora<sup>®</sup> wall base

## BASE

nora<sup>®</sup> wall base provides the finishing touch to any installation. Whether installed in a patient room, classroom, corridor or entranceway, nora wall base provides superb flexibility, scratch and scuff resistance.

- No color drift and no dye lots.
- UV resistance, color will not fade.
- Micro squared angled up—cut to minimize joint visibility.
- Stable dimensions—height, toe, gauge, etc.



### Product Data

Product	nora <sup>®</sup> wall base, Article 820
Description	nora <sup>®</sup> vulcanized rubber compound 999 with natural fillers and environmentally compatible color pigments that are free of toxic heavy metals like lead, cadmium or mercury.
Characteristics	<p>Material Dimensions:</p> <p>Length: 120 feet (36.6 m)</p> <p>Depth: 1.97 inches (50 mm)</p> <p>Height: 4 inches (102 mm)</p> <p>Thickness: 0.13 inches (3.2 mm)</p> <p>Dimensional Stability: Meets requirements</p> <p>Composition: Heterogeneous rubber compound</p> <p>Colors: 70 standard colors</p> <p>Surface: Smooth</p>

### Technical Data

ASTM F1861	Type TP, rubber, thermoplastic
Flammability	ASTM E648; NFPA 253; NBSIR 75 950, 0.99 Class 1, ≥ 0.45 watts/sq. cm is required
Smoke Density	ASTM E662; NFPA 256; NBS, 258 (flaming) and 273 (non-flaming) < 450 is required
Bacteria Resistance	ASTM E2180 and ASTM G21, resistant to bacteria, fungi, and micro-organism activity

### Environmental Attributes

VOC Emissions	Greenguard Gold certified for low VOC Emissions in compliance with California Department of Public Health (CDPH) Standard Method v1.1-2010
LEED Contribution	Meets VOC emissions requirements of LEED

## Installation

Site Conditions	The installation area must be fully enclosed, weather tight, and climate controlled between 63°F and 75°F and 40% to 60% ambient relative humidity (RH) for at least 48 hours prior, during and 72 hours after installation.
Adhesive	Use standard wall base adhesive; nora does not manufacture base adhesive
Unique Characteristics	Long runs with minimal seams Outside corners must be heated and formed, do not gouge and bend Additionally available in 2.5 and 6 inch heights, with no minimum order and a 3 week lead time. Custom color matching is also available.

For complete installation instructions, refer to the nora® Installation Guide.

## Care and Cleaning

Refer to the nora® Maintenance Guides.

## Storage

nora® flooring can be stored within a temperature range of -5°F (-21°C) to 120°F (49°C) under the following conditions: Pallets shall remain intact, undamaged, not be stacked, be in a permanently dry environment, and with no direct sunlight. However, all adhesives and cold weld must remain at room temperature without freezing.

## Warranty

Limited 5 year warranty. See nora® Limited Warranty.

For current nora® Installation Guides, Guide Specifications, Maintenance Guides, and Limited Warranties, please visit [www.nora.com/us](http://www.nora.com/us).

*Updated: November 2018*

### **nora systems, Inc.**

9 Northeastern Blvd.  
Salem, NH 03079  
Toll free: 800-332-NORA  
Phone: (603) 894-1021  
Fax: (603) 894-6615  
E-mail: [info-us@nora.com](mailto:info-us@nora.com)  
[www.nora.com/us](http://www.nora.com/us)