

# norament<sup>®</sup> 825 round TILE

Rubber floor covering for heavy traffic areas, with a classical round pastille, one-colored surface.

- Good for heavy traffic
- Superior footfall sound absorption
- Excellent slip resistance
- Increased safety thanks to high fire-retardant properties
- Seamless installation
- No coatings needed



## Product Data

Product	norament <sup>®</sup> 825 round 3.2 mm tile resilient floor covering, Article 1902
Description	nora <sup>®</sup> vulcanized rubber compound 925 with environmentally compatible color pigments that are free of toxic heavy metals like lead, cadmium or mercury.
Characteristics	Material Size: 19.72 inches by 19.72 inches (501 mm by 501 mm) Thickness: 0.13 inches (3.2 mm) Dimensional Stability: Meets requirements Composition: Homogeneous rubber compound Colors: 20 Standard Surface: Round

## Technical Data

Static Load Limit	ASTM F970, Residual compression of 0.004" with 800 lbs. ≤ 0.005" with 250 lbs. is required
Rolling Load Limit	≤ 550 lbs. /sq. inch; no forklift traffic
Slip Resistance	ASTM D2047 Static coefficient of friction, Neolite dry 0.76 Neolite wet 0.85 ≥ 0.5 is required
Flammability	ASTM E648; NFPA 253; NBSIR 75 950, 0.80 Class 1, ≥ 0.45 watts/sq. cm is required
Smoke Density	ASTM E662; NFPA 256; NBS, 413 (flaming) and 367 (non-flaming) < 450 is required
Bacteria Resistance	ASTM E2180 and ASTM G21, resistant to bacteria, fungi, and micro-organism activity
Sound Absorption	ISO 140, Lw12dB (compare only Δ values)
Hardness	ASTM D2240, Shore type "A", 89 achieved, ≥ 85 is required
CAN/ULC-S102.2	Surface Burning, FSC1 of 55 and SD of 450

## Environmental Attributes

Manufactured Without	PVC (polyvinyl chloride) Plasticizers (phthalates) Halogens (chlorine)
Production Plant Certifications	ISO 9001:2000 ISO 14001
VOC Emissions	CA 01350 Compliant

## Installation

Site Conditions	The installation area must be fully enclosed, weather tight, and climate controlled between 63°F and 75°F and 40% to 60% ambient relative humidity (RH) for at least 48 hours prior, during and 72 hours after installation.
Adhesive	Absorptive substrates: use nora® AC 100, PU 102 or dryfix 750 adhesives Non-absorptive substrates: use nora® PU 102 or dryfix 750 adhesives
Unique Characteristics	Welding not required

For complete installation instructions, refer to the nora® Installation Guide.

## Care and Cleaning

A post-installation cleaning must be performed before the area is occupied.

Refer to the norament® Maintenance Guides.

## Wheel Types

No metal or hard plastic wheels, the shape of the contact surface of wheels must be flat with round edges. The shore hardness must be type A ≤ 90.

## Storage

nora® flooring can be stored within a temperature range of -5°F (-21°C) to 120°F (49°C) under the following conditions: Pallets shall remain intact, undamaged, not be stacked, be in a permanently dry environment, and with no direct sunlight. However, all adhesives and cold weld must remain at room temperature without freezing.

## Warranty

Limited 10-year warranty. See nora® Limited Warranty.

For current nora® Installation Guides, Guide Specifications, Maintenance Guides, and Limited Warranties, please visit [www.nora.com/us](http://www.nora.com/us).

*Updated: September 2019*

### **nora systems, Inc.**

9 Northeastern Blvd.  
Salem, NH 03079  
Toll free: 800-332-NORA  
Phone: (603) 894-1021  
Fax: (603) 894-6615  
E-mail: [info-us@nora.com](mailto:info-us@nora.com)  
[www.nora.com/us](http://www.nora.com/us)