


norament[®] 992

TILE

Rubber flooring specially formulated for extreme resistance to ice blades, spikes, cleats and free weights.

- Good for maximum usage
- Superior footfall sound absorption
- Excellent slip resistance
- Increased safety thanks to high fire-retardant properties
- Seamless installation
- No coatings needed



Product Data

Product	norament [®] 992 9.0 mm tile resilient floor covering, Article 1955
Description	nora [®] vulcanized rubber compound 992 with environmentally compatible color pigments that are free of toxic heavy metals like lead, cadmium or mercury.
Characteristics	Material Size: 39.45 inches by 39.45 inches (1002 mm by 1002 mm) Thickness: 0.36 inches (9.0 mm) Dimensional Stability: Meets requirements Composition: Homogeneous rubber compound Colors: 1 Standard Surface: Hammered

Technical Data

Static Load Limit	ASTM F970, Residual compression of 0.005" with 800 lbs. ≤ 0.005" with 250 lbs. is required
Rolling Load Limit	≤ 850 lbs. /sq. inch; nora polyurethane adhesive is required
Slip Resistance	ASTM D2047 Static coefficient of friction, Neolite dry 0.93 Neolite wet 0.93 ≥ 0.5 is required (not recommended for ramps)
Flammability	ASTM E648; NFPA 253; NBSIR 75 950, 0.56 Class 1, ≥ 0.45 watts/sq. cm is required
Smoke Density	ASTM E662; NFPA 256; NBS, 289 (flaming) and 373 (non-flaming) < 450 is required
Bacteria Resistance	ASTM E2180 and ASTM G21, resistant to bacteria, fungi, and micro-organism activity
Sound Absorption	ASTM E2179; ISO 140, ΔLw17dB (compare only Δ values)
Hardness	ASTM D2240, Shore type "A", 77 achieved, ≥ 70 is required
CAN/ULC-S102.2	Surface Burning, FSC1 of 25 and SD of 332

Environmental Attributes

Manufactured Without	PVC (polyvinyl chloride) Plasticizers (phthalates) Halogens (chlorine)
Production Plant Certifications	ISO 9001:2000 ISO 14001
VOC Emissions	GREENGUARD Gold Certified for Low VOC Emissions CA 01350 Compliant

Installation

Site Conditions	The installation area must be fully enclosed, weather tight, and climate controlled between 63°F and 75°F and 40% to 60% ambient relative humidity (RH) for at least 48 hours prior, during and 72 hours after installation.
Adhesive	Use only nora® PU 102
Unique Characteristics	Welding not required Resists ice blades, spikes, cleats and free weights

For complete installation instructions, refer to the nora® Installation Guide.

Care and Cleaning

A post-installation cleaning must be performed before the area is occupied.

Refer to the norament® Maintenance Guides.

Wheel Types

No metal or hard plastic wheels, the shape of the contact surface of wheels must be flat with round edges. The shore hardness must be type A ≤ 90.

Storage

nora® flooring can be stored within a temperature range of -5°F (-21°C) to 120°F (49°C) under the following conditions: Pallets shall remain intact, undamaged, not be stacked, be in a permanently dry environment, and with no direct sunlight. However, all adhesives and cold weld must remain at room temperature without freezing.

Warranty

Limited 5-year warranty. See nora® Limited Warranty.

For current nora® Installation Guides, Guide Specifications, Maintenance Guides, and Limited Warranties, please visit www.nora.com/us.

Updated: November 2018

nora systems, Inc.

9 Northeastern Blvd.
Salem, NH 03079
Toll free: 800-332-NORA
Phone: (603) 894-1021
Fax: (603) 894-6615
E-mail: info-us@nora.com
www.nora.com/us