

norament arago nTx

Rubber tile floor covering combining a fine grain design and modern marbling with a flat, direction-oriented relief structure. No two tiles are the same – each tile is totally unique. This fast installation system pairs a nora® rubber floor covering with a factory-applied adhesive. The flooring is cleanly and safely installed in a few steps then immediately ready for use.



Product Data

Product: norament® arago™ nTx™ resilient tile floor covering, Article 3122

Description: nora® vulcanized rubber compound 926 with environmentally compatible color pigments that are free of toxic heavy metals like lead, cadmium, or mercury

Material Size: 39.53" x 19.76" (1004mm x 502mm)

Thickness: 0.14" (3.5mm)

Dimensional Stability: Meets requirements

Composition: Homogeneous rubber compound with a random scattered design

Colors: 2 Standard; additional color available with minimum order requirements

Surface: Relief Structure

Technical Data

Flammability (E648/NFPA 253): ≥ 0.45 watts/sq. cm for Class 1 is required	NBSIR 75 950, 0.98
Smoke Density (ASTM E662/NFPA 258): < 450 is required	NBS, 369 (flaming) and 205 (non-flaming)
Surface Burning (CAN/ULC-S102.2):	FSC1 of 75 and SD of 470
Slip Resistance (ASTM D2047): ≥ 0.5 is required	Static coefficient of friction, Neolite dry 0.81 Neolite wet 0.87
Bacteria Resistance (ASTM E2180/ASTM G21):	Resistant to bacteria, fungi, and micro-organism activity
Sound Absorption (ASTM E2179/ISO 10140-3):	ΔIIC 15, ΔLw 10dB (compare only Δ values)
Hardness (ASTM D2240): ≥ 70 is required	Shore type "A", 82
Static Load (ASTM F970): ≤ 0.005 inches with 250 lbs. is required	Residual compression of 0.004 inches with 800 lbs.
Rolling Load Limit (ASTM F2753):	≤ 850 lbs. / sq. inch; will accept forklift traffic
Abrasion Resistance (ASTM D3389): ≤ 0.035 oz. (1.0g) is required	1.1 lbs. (500g) load on H-18 wheel with 1000 cycles, 0.008 oz. (0.24g) weight loss
Oil & Grease Resistance (EN/ISO 26978):	Pass

Environmental Attributes

Carbon: All flooring products 3rd party verified carbon neutral throughout their entire life cycle through the Interface Carbon Neutral Floors™ program. Learn more at www.interface.com/carbonneutral.

Indoor Air Quality: GREENGUARD Gold Certified for low VOC emissions in compliance with CDPH 01350

Material Composition: Free of added formaldehyde, heavy metals and ortho-phthalates, fluorinated chemicals (PFAS), and halogenated flame retardants

Transparency: Cradle to Cradle v3.1 Silver, Environmental Product Declarations (EPDs), and Health Product Declarations (HPDs) available for standard norament and noraplan® floor coverings. Learn more at www.nora.com.

Production Plant Certifications: ISO 9001:2000, ISO 14001

Installation

Site Conditions: The installation area must be fully enclosed, weather tight, and climate controlled between 63°F and 75°F and 40% to 60% ambient relative humidity (RH) for at least 48 hours prior, during and 72 hours after installation.

Adhesive: Factory-applied

Unique Characteristics:

- Good for very heavy traffic
- Superior footfall sound absorption
- Superior slip resistance
- High fire-retardant properties
- Monolithic seamless installation with coordinating weld
- Welding not required, unless specified
- No moisture limit or testing required
- Immediately open to traffic with no down time
- Tile design allows for various design layouts, as well as the flexibility to change the aesthetic by adding a beveled edge (Art. 3119)

For complete installation instructions refer to the nora nTx Installation Instructions.

Care and Cleaning

No finishes/coatings or harsh chemicals necessary. A post-installation cleaning must be performed before the area is occupied. Refer to the nora Maintenance Guidelines.

Wheel Types

No metal or hard plastic wheels, the shape of the contact surface of wheels must be flat with round edges. The shore hardness must be type A ≤ 90.

Storage

nora nTx flooring can be stored within a temperature range of 50°F (10°C) to 80°F (27°C) under the following conditions: Pallets must remain intact with sheet goods standing on end, undamaged, not be stacked, be in a permanently dry environment, and with no direct sunlight. However, all adhesives and cold weld must remain at room temperature without freezing.

Warranty

Limited 10-year bond warranty and 15-year warranty. Refer to the nora nTx and nora Product Warranties - Americas.

Current nora Installation Instructions, Guide Specifications, Maintenance Guidelines, and Product Warranties, can be found at www.nora.com.

nora®, norament®, and noraplan® are trademarks owned by nora systems GmbH and registered in the United States, Canada, and other countries. All other trademarks are the property of their respective owners.

Updated: June 2022

nora systems, Inc.
9 Northeastern Blvd.
Salem, NH 03079
T: 800.332.NORA
T: 603.894.1021
info-us@nora.com
www.nora.com

nora®
by **Interface**®