


# norament satura nTx

Rubber tile floor covering with a tone-in-tone granular design and a hammered surface. This fast installation system pairs a nora® rubber floor covering with a factory-applied adhesive. The flooring is cleanly and safely installed in a few steps then immediately ready for use.



## **Product Data**

Product: norament® satura™ nTx™ resilient tile floor covering, Article 3111

Description: nora® vulcanized rubber compound 926 with environmentally compatible color pigments that are free of toxic heavy metals like lead, cadmium, or mercury

Material Size: 39.53" x 39.53" (1004mm x 1004mm)

Thickness: 0.14" (3.5mm)

Dimensional Stability: Meets requirements

Composition: Homogeneous rubber compound with a random scattered design

Colors: 2 Standard; additional colors available with minimum order

Surface: Hammered

## **Technical Data**

Flammability (E648/NFPA 253): ≥ 0.45 watts/sq. cm for Class 1 is required	NBSIR 75 950, 0.97
Smoke Density (ASTM E662/NFPA 258): < 450 is required	NBS, 267 (flaming) and 130 (non-flaming)
Surface Burning (CAN/ULC-S102.2):	FSC1 of 75 and SD of 470
Slip Resistance (ASTM D2047): ≥ 0.5 is required	Static coefficient of friction, Neolite dry 0.99 Neolite wet 0.95
Bacteria Resistance (ASTM E2180/ASTM G21):	Resistant to bacteria, fungi, and micro-organism activity
Sound Absorption (ASTM E2179/ISO 10140-3):	ΔIIC 11, ΔLw 11dB (compare only Δ values)
Hardness (ASTM D2240): ≥ 70 is required	Shore type "A", 82
Static Load (ASTM F970): ≤ 0.005 inches with 250 lbs. is required	Residual compression of 0.005 inches with 800 lbs.
Rolling Load Limit (ASTM F2753):	≤ 850 lbs. / sq. inch; will accept forklift traffic
Abrasion Resistance (ASTM D3389): ≤ 0.035 oz. (1.0g) is required	1.1 lbs. (500g) load on H-18 wheel with 1000 cycles, 0.002 oz. (0.05g) weight loss
Oil & Grease Resistance (EN/ISO 26978):	Pass

## **Environmental Attributes**

Carbon: All flooring products 3rd party verified carbon neutral throughout their entire life cycle through the Interface Carbon Neutral Floors™ program. Learn more at [www.interface.com/carbonneutral](http://www.interface.com/carbonneutral).

Indoor Air Quality: GREENGUARD Gold Certified for low VOC emissions in compliance with CDPH 01350

Material Composition: Free of added formaldehyde, heavy metals and ortho-phthalates, fluorinated chemicals (PFAS), and halogenated flame retardants

Transparency: Cradle to Cradle v3.1 Silver, Environmental Product Declarations (EPDs), and Health Product Declarations (HPDs) available for standard norament and noraplan® floor coverings. Learn more at [www.nora.com](http://www.nora.com).

Production Plant Certifications: ISO 9001:2000, ISO 14001

## **Installation**

Site Conditions: The installation area must be fully enclosed, weather tight, and climate controlled between 63°F and 75°F and 40% to 60% ambient relative humidity (RH) for at least 48 hours prior, during and 72 hours after installation.

Adhesive: Factory-applied

Unique Characteristics:

- Good for very heavy traffic
- Superior footfall sound absorption
- Superior slip resistance
- High fire-retardant properties
- Monolithic seamless installation with coordinating weld
- Welding not required, unless specified
- No moisture limit or testing required
- Immediately open to traffic with no down time

For complete installation instructions refer to the nora nTx Installation Instructions.

## **Care and Cleaning**

No finishes/coatings or harsh chemicals necessary. A post-installation cleaning must be performed before the area is occupied. Refer to the nora Maintenance Guidelines.

## **Wheel Types**

No metal or hard plastic wheels, the shape of the contact surface of wheels must be flat with round edges. The shore hardness must be type A  $\leq$  90.

## **Storage**

nora nTx flooring can be stored within a temperature range of 50°F (10°C) to 80°F (27°C) under the following conditions: Pallets must remain intact with sheet goods standing on end, undamaged, not be stacked, be in a permanently dry environment, and with no direct sunlight. However, all adhesives and cold weld must remain at room temperature without freezing.

## **Warranty**

Limited 10-year bond warranty and 15-year warranty. Refer to the nora nTx and nora Product Warranties - Americas.

Current nora Installation Instructions, Guide Specifications, Maintenance Guidelines, and Product Warranties, can be found at [www.nora.com](http://www.nora.com).

nora®, norament®, and noraplan® are trademarks owned by nora systems GmbH and registered in the United States, Canada, and other countries. All other trademarks are the property of their respective owners.

Updated: June 2022