

nora[®] L 1000

High performance self-leveling compound

nora[®] ONE

nora one[®] system components are only eligible for jobs that meet the minimum requirements of 50,000 square feet.

nora[®] L 1000 leveler is a cementitious, self-leveling compound formulated for use at depths up to 1/2" (12 mm) producing a smooth, flat surface for nora[®] rubber flooring installations. nora L 1000 leveler requires the use of nora[®] PRN 102 primer for non-absorptive substrates or wood or nora[®] PRP 101 primer for absorptive substrates prior to application, and following the nora[®] Installation Guide.

- Fast setting formula
- Ready for installation after 24 hours
- Up to 1 inch deep in one application
- Superior bonding to a wide range of substrates
- Meets VOC content requirements of LEED, including REACH

nora L 1000 – Art. 6697

Shelf Life	6 Months
Application	Guage rake and spiked roller
Coverage	58 sq. ft. at 1/8" depth, 29 sq. ft. at 1/4" depth; coverage will vary based on substrate conditions
Water Ratio	6 - 6.5 quarts of clean water per 50 lb. bag
Working Time	20 - 40 Minutes
Dry Time	2 - 3 hours for light foot traffic, depending on thickness, porosity, temperature, and humidity; 24 hours dry time required to install flooring
Storage	Room temperature and away from direct sunlight
Moisture Limit	Up to 85% RH following ASTM F2170 <i>Standard Test Method for Determining Relative Humidity in Concrete Floor Slabs Using in situ Probes</i>
Compressive Strenght	4,350 psi after 28 days as per ASTM C109M

For information on the nora one[®] system solution visit www.nora.com/us/noraone

nora systems, Inc.

9 Northeastern Blvd.
Salem, NH 03079
Toll free: 800-332-NORA
Phone: (603) 894-1021
Fax: (603) 894-6615
E-mail: info-us@nora.com
www.nora.com/us

nora[®]
by Interface[®]