

Technical data

norament® 975 LL, surface: hammerblow

	Test method	Requirements	Average test results from running production
CE conformity	EN 14041		Manufacturer: nora systems GmbH, D-69469 Weinheim
DoP-No.	EN 14041		0024
Thermal conductivity	EN 10456	$\lambda = 0.17 \text{ W/(m·K)}$	Fulfilled
Dynamic coefficient of friction	EN 13893	DS	Fulfilled
Reaction to fire	EN 13501-1	Not bonded	Bi-s1

Properties acc. to EN 1817

Thickness	EN ISO 24346	Mean value $\pm 0.15 \text{ mm}$ acc. to EN 1817	3.5 mm
Dimensional stability	EN ISO 23999	$\pm 0.4 \%$	$\pm 0.1 \%$
Cigarette-burn resistance	EN 1399	Procedure A (stubbed out) \geq level 4 Procedure B (burning) \geq level 3	Fulfilled
Flexibility	EN ISO 24344, procedure A	Mandrel diameter 20 mm, no fissuring	Fulfilled
Hardness	ISO 48-4	≥ 75 Shore A acc. to EN 1817	85 Shore A
Residual indentation	EN ISO 24343	Mean value $\leq 0.25 \text{ mm}$ at thickness $\geq 3.0 \text{ mm}$	0.07 mm
Abrasion resistance at 5 N load	ISO 4649, procedure A	$\leq 250 \text{ mm}^3$	120 mm ³
Colour fastness to artificial light	ISO 105-B02, procedure 3, test conditions 6.1 a)	At least level 6 on the blue scale; \geq level 3 on the grey scale	Grey scale \geq level 3 acc. to ISO 105-A02
Classification	EN ISO 10874	Commercial / Industrial	34 / 43

Additional technical properties

Anti-slip properties	DIN EN 16165	Acc. to DGUV 108-003	R 9
Improvement in footfall sound absorption	ISO 10140-3		8 dB
Effect of chemicals	EN ISO 26987		Resistant depending on concentration and time of exposure*
Electrical insulation properties	EN 1081 R1		$> 10^9 \text{ Ohm}$
Electrical propensity when walked upon	EN 1815		Antistatic, charging in case of rubber soles $< 2 \text{ kV}$
Effect of a castor chair	EN ISO 4918		Suitable if castor wheels, type W, acc. to EN 12529, are used
Underfloor heating	EN 1264-2		Suitable, max. 35 C°

* In case of increased impact of oils, grease, acids, alkalis and other aggressive chemicals please contact us.

EN 1817: Specification for homogeneous and heterogeneous smooth elastomer floor coverings

Colour variations due to different production batches as well as technical alterations to improve the product have to be accepted.



www.blauer-engel.de/uz120

